Nexus Pump and Valve Packing



DATA SHEET



Nexus Style 2361 Packing

Description

Style 2361 packing is a Graphite enhanced Expanded PTFE braided packing with an Aramid fibre reinforcement in the four corners. Style 2361 has been formulated to improve the abrasion resistance of standard graphite encapsulated PTFE (Style 2301) packing. This product is a dense and resilient product with the ability to withstand extrusion and abrasive wear while able to run at high speed due to the combination of graphite encapsulated PTFE and Aramid fibre.

Construction

Style 2361 is a braided packing constructed of a combination of Graphite filled Expanded PTFE and Aramid yarn which have been inter-braided into a dense, but flexible product. PTFE tape and Graphite have been locked together in such a manner that the maximum benefits are gained from both these wonderful materials. There are no added lubricants that can migrate out of this product; the lubrication is included in the yarn.

Application

Style 2361 is ideally suited for pump applications due to its material characteristics. The ability of the base material (Graphite filled Expanded PTFE) to remove heat from the surface contact area, while remaining flexible, makes this one of Industry's most widely used gland packing materials. Use in valves has also proven most successful due to the dense construction of the yarn, allowing no penetration by the sealed medium. This product is used throughout all the different industries in almost every application imaginable, limited only by severe temperature and very strong oxidizers such as fuming Nitric Acid, Fluorine, Aqua Regia and Oleum.

Size and Weight

Style 2361 Packing										
mm	3	4	5	6	7	8	10	11	12	13
inch	1/8	5/32	3/16	1/4		5/16	3/8	7/16	1/2	
m/kg	70	32	27	17	13.6	10.5	7	5.51	4.5	4
mm	14	15	16	18	19	20	22	24	25	
Inch	9/16		5/8	11/16	3/4	13/16	7/8	15/16	1	
m/kg	3.3	3	2.6	2	1.8	1.6	1.38	1.16	1.03	

Specification

<u>Item</u>	<u>Unit</u>		Magnitude	
Dimensional Deviation	mm	Axial	0.00 ~ +0.50	
Differsional Deviation	mm	Radial	0.00 ~ -0.50	
Working Temperature	°C	-100 ~ +250		
Pressure	bar	25	Rotary (Pumps)	
Pressure	Dai	200	Stationary (Valves)	
Surface Speed	m/sec	15		
рН	рН	2 - 12		
Base Yarn	Graphite fi	Graphite filled PTFE and Aramid		
Lubrication		Zero External		